



# AURELIA® BOLD

5mil, Nitrile Powder Free Examination Gloves

## AURELIA® GLOVES

A SUPERMAX HEALTHCARE BRAND

sales@supermax.co.uk  
+441733 615215

Supermax Healthcare Ltd,  
Unit 12-16 Titan Drive  
Fengate, Peterborough  
PE1 5XN

[aureliagloves.co.uk](http://aureliagloves.co.uk)

Regulations	PPE Reugulation (EU) 2016/425 Medical Device Regulation (EU) 2017/745, 93/42/EEC
Quality Standards	ISO 9001:2015 Quality Management Systems ISO 13485: 2016 Medical Devices Quality Management Systems
Harmonised Standards	BS EN ISO 374 - 1,2,4,5 Protective gloves against dangerous chemicals and microorganisms. BS EN 455 1-4 Medical gloves for single use. EN 420: 2003 + A1: 2009 Protective gloves. General requirements and test methods. BS EN 1186: 2002. Materials and articles in contact with foodstuffs.

 10 x 100















**S M L XL XXL**  
 73996 73997 73998 73999 73990

Sizes & Dimensions	Single wall thickness	Physical Properties												
 <p>XS 70+10 mm S 80+10 mm M 95+10 mm L 110+10 mm XL &gt; 110 mm</p>	 <p>min. 240 mm</p>  <p>① min. 0.13 mm ② min. 0.10 mm ③ min. 0.08 mm</p>	<table border="1"> <thead> <tr> <th></th> <th>Unaged</th> <th>Aged</th> </tr> </thead> <tbody> <tr> <td>Tensile Strength</td> <td>Min. 14.0 MPa</td> <td>Min. 14.0 MPa</td> </tr> <tr> <td>Elongation</td> <td>Min. 500%</td> <td>Min. 400%</td> </tr> <tr> <td>Strength at Break</td> <td>Min. 6N</td> <td>Min. 6N</td> </tr> </tbody> </table>		Unaged	Aged	Tensile Strength	Min. 14.0 MPa	Min. 14.0 MPa	Elongation	Min. 500%	Min. 400%	Strength at Break	Min. 6N	Min. 6N
	Unaged	Aged												
Tensile Strength	Min. 14.0 MPa	Min. 14.0 MPa												
Elongation	Min. 500%	Min. 400%												
Strength at Break	Min. 6N	Min. 6N												



Nitrile



Powder Free



5 Years



Micro



5.5g +/- 0.2g



Black

